



PRODUCT DATA SHEET

Product Description

A high quality, acrylic paint for interior/exterior applications. For use on walls and ceilings of primed plaster, wallboard, wood, masonry and primed metal. Hiding and sheen are such that application of one coat is usually sufficient.

Uses

A fast drying flat latex designed for all interior applications where a high hiding product is required.

Technical Data

Type: Acrylic
 Gloss/Sheen: Between Flat and Eggshell
 Colour: White
 Tint Range: As required
 Recommended Number Of Coats: 1
 Theoretical Coverage: 400-500ft² (37-45m²) per US gal @ 4mils wet
 Density: 11.4.2±0.2 lbs/gal
 Weight Solids: 52.1±0.2%
 Volume Solids: 42.4±0.2%
 VOC: <50 g/L
 Specific Gravity: 1.37

Surface Preparation

Surfaces must be clean and dry and free from dust, grease and other contaminants. All surface contamination shall be removed by washing with an appropriate cleaner, rinsed thoroughly and allowed to dry. Any peeling paint shall be sanded. All glossy surfaces shall be sanded dull. Stains from water, smoke, grease, etc. shall be sealed with an appropriate primer/sealer. Clean all sanding dust as it will decrease adhesion.

For drywall fill all cracks and nail holes with a patching compound and sand smooth. Any joint compound must be cured and sanded smooth. Clean all sanding dust.

For masonry, concrete, cement and block all surfaces must be cured as per the supplier's recommendations. All form and release agents must be removed. Rough surfaces can be filled to provide a smooth surface.

For plaster surfaces, bare plaster shall be cured and hard.

For wood surfaces, any exposed wood shall be sanded to a fresh surface. Use a wood filler or putty to fill all holes/imperfections and sand smooth. Remove all sanding dust.

Application & Clean Up

Brush, roll or spray
 Touch: 15-30 minutes
 Recoat: 1-2 hours
 Drying and recoat times are temperature, humidity and film thickness dependent.

Miscellaneous Information

If mildew is present, surface should be washed using a bleach solution. Apply solution and scrub area affected. Allow solution to remain for 10 minutes on surface and then rinse thoroughly with water. Allow surface to dry completely before painting.